LG CHEM POLAND SP. Z O.O
UL. LG 3, BISKUPICE PODGORNE,
55-040 KOBIERZYCE, POLAND
FAX :48-71-733-8200
TEL :48-71-733-8175

PROPERTY REPORT

SHIPMENT NO.		PRODUCT	EPC	GRADE	LUPOY GN5201F E4650 1000KG FLECON
LOT NO.	P22112H	QUANTITY (KG)	1000	DELIVERY DATE	07.03.2022
CUSTOMER		Curtis Development Sp. z o.o.			

TYPICAL VALUES

PROPERTY	TEST METHOD	TEST CONDITION	UNIT	RESULT
Impact Strength(Izod)	ASTM D256	1/8″,NOTCHED	Kgfc/c	10.4
Tensile Strength	ASTM D638	50MM/MIN	kgf/cm2	1002
Flexural Strength	ASTM D790	1/8″,SPAN50,10mm/min	kgf/cm2	1483
Flexural Modulus	ASTM D790	1/8″,SPAN50,10mm/min	kgf/cm2	61054

THIS CERTIFICATION IS SUBJECT TO OUR STANDARD TEST CONDITION AND TEST MACHINE.

ISSUED BY

LG CHEM POLAND SP. Z O.O.
QA MANAGER